



Products and Classification	Extra Flex	LCP	RP	RSP	RSP AL	RAP	RAP 45	RAP 60	Quick Set
	Aromatic Polyurea					Aliphatic Polyurea			Aromatic Epoxy
Chemicals									
Acetic Acid (100%)	C	C	C	RC	RC	C	C	C	R
Acetone	C	C	C	RC	RC	C	C	C	R
Ammonium Hydroxide (50%)	RC	RC	RC	R	R	RC	RC	RC	R
Benzene	C	C	C	RC	RC	C	C	C	Contact EPI
Brine-Saturated (310 g/l)	R	R	R	R	R	R	R	R	R
Chlorinated Water	R	R	R	R	R	R	R	R	Contact EPI
Clorox® (10%) Water	R	R	R	R	R	R	R	R	Contact EPI
Diesel Fuel	RC	RC	RC	RC	RC	RC	RC	RC	Contact EPI
Gasoline	RC	RC	RC	RC	RC	RC	RC	RC	R
Gasoline/5% MTBE	RC	RC	RC	RC	RC	RC	RC	RC	R
Gasoline/5% Methanol	RC	RC	RC	RC	RC	RC	RC	RC	Contact EPI
Hydrochloric Acid (37%)	R	R	R	R	R	R	R	R	R
Hydrofluoric Acid (10%)	NR	NR	NR	R	R	NR	NR	NR	R
Hydraulic Fluid (oil)	RC	RC	RC	RC	RC	RC	RC	RC	R
Isopropyl Alcohol	R	R	R	R	R	R	R	R	R
Lactic Acid	RC	RC	RC	RC	RC	RC	RC	RC	Contact EPI
MEK	RC	RC	RC	RC	RC	RC	RC	RC	R
Methanol	R	R	R	R	R	R	R	R	R
Methylene Chloride	C	C	C	C	C	C	C	C	Contact EPI
Mineral Spirits	RC	RC	RC	RC	RC	RC	RC	RC	Contact EPI
Motor Oil	R	R	R	R	R	R	R	R	R
MTBE	C	C	C	C	C	C	C	C	Contact EPI
Muriatic Acid (10%)	R	R	R	R	R	R	R	R	R
Sodium Chloride (10%)	R	R	R	R	R	R	R	R	R
Nitric Acid (20%)	NR	NR	NR	R	R	NR	NR	NR	RC
Phosphoric Acid (10%)	R	R	R	R	R	R	R	R	R
Phosphoric Acid (50%)	NR	NR	NR	R	R	NR	NR	NR	R
Potassium Hydroxide (10%)	R	R	R	R	R	R	R	R	R
Potassium Hydroxide (20%)	R, Dis	R, Dis	R, Dis	R, Dis	R, Dis	R, Dis	R, Dis	R, Dis	R, Dis
Propylene Carbonate	RC	RC	RC	RC	RC	RC	RC	RC	Contact EPI
Skydrol ®	C	C	C	C	C	C	C	C	R
Sodium Hydroxide, pH 12	R	R	R	R	R	R	R	R	R
Sodium Hydroxide (50%)	R, Dis	R, Dis	R, Dis	R	R	R, Dis	R, Dis	R, Dis	R, Dis
Sodium Hypochlorite (10%)	R	R	R	R	R	R	R	R	R
Sodium Bicarbonate	R	R	R	R	R	R	R	R	R
Stearic Acid	R	R	R	R	R	R	R	R	R
Sugar/Water	R	R	R	R	R	R	R	R	R
Sulfuric Acid (10%)	R	R	R	R	R	R	R	R	R
Sulfuric Acid (>50%)	RC	RC	RC	R	R	RC	RC	RC	R
Toluene	R	R	R	R	R	R	R	R	Contact EPI
1,1,1-Trichloroethane	C	C	C	C	R	C	C	C	Contact EPI
Trisodium Phosphate	R	R	R	R	R	R	R	R	R
Vinegar/Water (5%)	R	R	R	R	R	R	R	R	R
Water	R	R	R	R	R	R	R	R	R
Water; (14 days @82C)	RC	RC	RC	R	R	RC	RC	RC	Contact EPI
Xylene	RC	RC	RC	RC	RC	RC	RC	RC	RC

Guide Key

R	Recommended, little or no visible damage
RC	Recommended Conditional, some effect, swelling, discoloration
C	Conditional, Crackling-wash down within 1 hour of spillage to avoid effects
NR	Not Recommended
DIS	Discoloration

** This guide is for general information only. Please contact an EPI representative to select the optimum product for your needs and budget.*