



Engineered Polymers, LLC.
2842 Progress Road
Madison, WI 53716

Phone: (608) 661-2800
Fax: (608) 661-2817
www.engineeredpolymers.net

REACTAMINE[®] POLYUREA EP-3014 SP

CODE: EP-3014 SP

PRODUCT DESCRIPTION:

EP-3014 SP is an aromatic polyurea modification with a silicone backbone. *EP-3014 SP* can be adjusted from 30 seconds to 30 minutes gel times. *EP-3014 SP* may be sprayed, rolled or brushed. *EP-3014 SP* is moisture insensitive and produces a very low exotherm in large masses. *EP-3014 SP* is a prepolymer with maximum free monomer levels of less than 0.1%

APPLICATIONS:

Flooring, Primers, Adhesives, Castings, Carpet Backing and Non-skid applications.

Tensile Strength	800 -1200 PSI
% Elongation @ Break	1000 -1200 %
Hardness Shore A	40 -50 A
Pot Life	1 to 30 Minutes
Tack Free Time	2 to 60 Minutes
Ratio	8/1 A/B PBV
Abrasion Taber HS17 Wheel 1000 Cycles	35 mgs

- Available clear (has amber tint) and in a variety of colors

Notice:

The information describing the physical properties made from these chemicals is offered in good faith and should be used only as a guide for design requirements. Results may vary due to different equipment and conditions. **EP** makes no warranty expressed or implied of its products and shall not be liable for direct, indirect or consequential damages in any event.